



AZM Pearl Supple DK

Technical Data

Looselay Dryback : 7 x 48 in 5mm Thickness 5/ 0.5 Wearlayer

Property	Result	Standard
Thickness	Average : 5.06 mm	ISO 24346
Squareness	MD max : 0.06mm, AMD max : 0.05mm	ISO 24342:2007+A1:2012
Straightness	MD max : 0.06mm, AMD max : 0.05mm	ISO 24342:2007+A1:2012
Dimentional Stability after exposure to heat	MD:0.07% AMD:0.04%	ISO 24399
Residual Indentation	0.05mm	ISO 24343-1
Color Fastness to artifical light	> Grade 6	ISO 24343-1:2007
Reaction to fire	Class Bf1 Critical flux $\geq 8.0 \text{ kW/m}^2$, FS ≤ 150 mm within 20s	EN 13501-1:2007+A1:2009
wear resistance	Wear Group: T	EN 660-2 : 1999+A1: 2003
Dynamic coefficient of friction	Longitudinal : 0.62 Width : 0.65	EN 13893 : 2008
Slip resistance	R10	DIN 51130 : 2010
Flexicity	No craxk was found	EN435
Phtalates (6 type)	N.D	EN 14372:2004
Formaldehyde	0.002 mg/m3	EN 717-1
TVOC	< 0.5 mg/m3	CDPH/EHLB Standard Methodv1.2-2017

