

AZM PEARL ECO LVT

Tehnickal Parameter		
Characteristics	Test Method	Result
Dimension	EN427	45x92 cm 18x121 cm
Thickness in total	EN428	5mm
Thickness of wear layers	EN429	0,5mm / 0,70mm
Total weight	EN430	9≥kg/m ²
Peeling stength of layers	EN431	pass
Shear forces of layer	EN432	Good
Shrinkage and bending	EN434	Shrinkage <0,1 % curling < 2mm
Elastic bending	EN434	No damage
Chemical corrosion	EN423	class 0
Residual indentation after static load	EN433	0,1 mm
Bearing a castor chair	EN435	No disturbance No delamination
Color fastness	ISO 105B02	>6
Wearability	EN660	pass
Toxic element test	EN71-3	Complies
Flame rating	ASTM E84-03	NFPA class B
Nonskid property	DIN 51130	R9
Performance classification	EN685	23,34,43
PVC block material performance testing GB8624 B1 grade flammability test		pass
CNS 8907 andi-flaming testing		pass

