



All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com/disclaimer.

Product noraplan uni **Colour** Saffron **Collection** noraplan **Format** Sheet **Surface**

Smooth **Product Options** Standard **Thickness** 2.0mm

Product Specifications

Article Number	1461
Format	Sheet
Size	1220 mm x 12.0 m
Surface	Smooth

CE Conformity

CE Conformity (EN 14041)	Manufacturer: nora systems GmbH, D-69469 Weinheim
DoP-No. (EN 14041)	0018
UK DoP-No. (EN 14041)	0018
Thermal conductivity (EN 10456)	Fulfilled ($\lambda = 0.17 \text{ W/(m}\cdot\text{K)}$)
Dynamic Coefficient of Friction (EN 13893)	Fulfilled (DS)
Reaction to fire (EN 13501-1)	Bfl-s1, bonded (Not bonded)

Performance Specifications

Reaction to fire (EN 13501-1)	Bfl-s1, bonded (Not bonded) Bfl-s1 (Bonded on mineral subfloor)
Thickness (EN ISO 24346)	(Mean value $\pm 0.15 \text{ mm}$) 2.0 mm
Dimensional stability (EN ISO 23999)	($\pm 0.4 \%$) $\pm 0.2 \%$
Cigarette-burn resistance (EN 1399)	Fulfilled (Procedure A (stubbed out) level ≥ 4 , Procedure B (burning) level ≥ 3)
Flexibility (EN ISO 24344, procedure A)	Fulfilled (Mandrel diameter 20 mm, no fissuring)
Hardness (ISO 48-4)	94 Shore A ($\geq 75 \text{ Shore A}$)
Residual indentation (EN ISO 24343)	(Mean value $\leq 0.15 \text{ mm}$ at thickness $< 2.5 \text{ mm}$) 0.03 mm
Abrasion resistance at 5 N load (ISO 4649, procedure A)	($\leq 250 \text{ mm}^3$) 130 mm^3
Colour fastness to artificial light (ISO 105-B02, procedure 3, test conditions 6.1 a))	Fulfilled Grey scale $\geq$ level 3 acc. to ISO 105-A02 (At least level 6 on the blue scale; $\geq$ level 3 on the grey scale)
Classification (EN ISO 10874)	34/42 (Commercial/Industrial)
Toxicity of fire gases (DIN 53436)	Carbonisation gases are non-toxic
Anti-slip properties (DIN EN 16165)	R9 (According to DGUV 108-003)
Improvement in footfall sound absorption (ISO 10140-3)	6 dB
Effect of chemicals (EN ISO 26987)	Resistant depending on concentration and time of exposure. In case of increased impact of oils, greases, acids, alkalis and other aggressive chemicals please contact us.
Electrical insulation properties (EN 1081 R1)	$> 10^9 \text{ Ohm}$
Electrical propensity when walked upon (EN 1815)	Antistatic, charging in case of rubber soles $< 2 \text{ kV}$
Effect of a castor chair (EN ISO 4918)	Suitable if castor wheels, type W, according to EN 12529 are used
Underfloor heating (EN 1264-2)	Suitable, max. $35 \text{ }^\circ\text{C}$

Health + Environmental Specifications

Environmental Product Declaration	noraplan uni
Indoor Air Quality & Environmental Certifications	Etiquetage A+ Byggsvarubedömningen Cradle to Cradle Certified Silver Singapore Green Building Product Blue Angel Indoor Air Comfort Gold eco-bau Austrian eco-label Greenguard Gold M1
Environmental Certifications	nora Cradle to Cradle Certified Silver
Embodied Carbon (Cradle to Gate)	9.63 kg CO ₂ eq./m ²

Technical Information

Installation	Installation recommendations
Maintenance	Cleaning recommendations
NCS-Codes	Download nora NCS-Codes
Warranty	End User Product Warranty
Manufacturing Location	ISO 9001, 14001 & 50001 Certified Facilities in Germany

Accessories

nora Accessories	Download PDF
------------------	------------------------------

Downloads

nora Viewbook	Download Viewbook
nora Lookbook	Download Lookbook
nora Product Catalogue	Download Product Catalogue

Certifications

