
norament 926 grano

Interface



All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com/disclaimer.

Product norament 926 grano **Colour** Blue Tansy **Collection** norament **Format** Tile

Surface Hammerblow **Product Options** Standard **Thickness** 3.5mm

Product Specifications	
Article Number	1911
Format	Tile
Size	610 mm x 610 mm
Surface	Hammerblow

CE Conformity	
CE Conformity (EN 14041)	Manufacturer: nora systems GmbH, D-69469 Weinheim
DoP-No. (EN 14041)	0021
UK DoP-No. (EN 14041)	0021
Thermal conductivity (EN 10456)	Fulfilled (λ = 0.17 W/(m·K))
Dynamic Coefficient of Friction (EN 13893)	Fulfilled (DS)
Reaction to fire (EN 13501-1)	Cfl-s1 (Not bonded)

Performance Specifications	
Reaction to fire (EN 13501-1)	Cfl-s1 (Not bonded) Bfl-s1 (Bonded on mineral subfloor)
Thickness (EN ISO 24346)	(Mean value ± 0.15 mm) 3.5 mm
Dimensional stability (EN ISO 23999)	(± 0.4 %) ± 0.2 %
Cigarette-burn resistance (EN 1399)	Fulfilled (Procedure A (stubbed out) level ≥ 4, Procedure B (burning) level ≥ 3)
Flexibility (EN ISO 24344, procedure A)	Fulfilled (Mandrel diameter 20 mm, no fissuring)
Hardness (ISO 48-4)	82 Shore A (≥ 75 Shore A)
Residual indentation (EN ISO 24343)	(Mean value ≤ 0.20 mm at thickness ≥ 3.0 mm) 0.12 mm
Abrasion resistance at 5 N load (ISO 4649, procedure A)	(≤ 250 mm^3) 115 mm^3
Colour fastness to artificial light (ISO 105-B02, procedure 3, test conditions 6.1 a))	Fulfilled Grey scale ≥ level 3 acc. to ISO 105-A02 (At least level 6 on the blue scale; ≥ level 3 on the grey scale)
Classification (EN ISO 10874)	34/43 (Commercial/Industrial)
Toxicity of fire gases (DIN 53436)	Carbonisation gases are non-toxic
Anti-slip properties (DIN EN 16165)	R10 (According to DGUV 108-003)
Improvement in footfall sound absorption (ISO 10140-3)	10 dB
Effect of chemicals (EN ISO 26987)	Resistant depending on concentration and time of exposure. In case of increased impact of oils, greases, acids, alkalis and other aggressive chemicals please contact us.
Electrical insulation properties (EN 1081 R1)	> 10^9 Ohm
Electrical propensity when walked upon (EN 1815)	Antistatic, charging in case of rubber soles < 2 kV
Effect of a castor chair (EN ISO 4918)	Suitable if castor wheels, type W, according to EN 12529 are used
Underfloor heating (EN 1264-2)	Suitable, max. 35 C°

Health + Environmental Specifications	
Environmental Product Declaration	Download EPD
Disclosure of Product Ingredients	Health Product Declaration
Indoor Air Quality & Environmental Certifications	Etiquetage A+ Byggvarubedömningen Austrian eco-label Blue Angel Cradle to Cradle Silver DGNB Navigator eco-bau Global Green Tag Greenguard Gold Indoor Air Comfort Gold M1 PEFC Singapore Greenbuilding
Environmental Certifications	Cradle to Cradle Silver
Embodied Carbon (Cradle to Gate)	14.1 kg CO_2 eq./m^2

Technical Information	
Installation	Installation recommendations
Maintenance	Cleaning recommendations
NCS-Codes	Download nora NCS-Codes
Warranty	End User Product Warranty
Manufacturing Location	ISO 9001, 14001 & 50001 Certified Facilities in Germany

Downloads	
nora Viewbook	Download Viewbook
nora Lookbook	Download Lookbook
nora Product Catalogue	Download Product Catalogue

Certifications